



TECHNICAL DATA SHEET

MARBLE GROUND


Marble-coarse

General Properties

Marble ground from MAYN is a natural product that is extracted from quarries in Egypt. It is ground according to industry's requirements. Sieves are used to give particle size distribution (PSD). It is used in oil and gas drilling processes

Chemical Composition

IUPAC Name	Chemical Formula	Weight (%)
Calcium oxide	CaO	40.0%
Magnesium carbonate	MgCO ₃	30.0%
Silicon dioxide	SiO ₂	22.0%
Aluminum oxide	Al ₂ O ₃	3.0%
Iron (III) oxide	Fe ₂ O ₃	2.0%
Sodium oxide	NaO	2.0%
Magnesium oxide	MgO	2.0%



Physical Properties

Specific gravity	2.69 g/cm ³
Hardness (Moh's)	4
PH	< 7.0
D (97)	315 µM (Micron)
D (50)	50 µM (Micron)
Maximum size	700 µM (Micron)

Type of Packing

Jumbo bag	
PP bag 25 kg	
Particle Size Range	Weight (%)
0.00 – 50 µM	< 50.0%
50 – 315 µM	> 47.0%
315 – 700 µM	< 3.00%

Sieve	ISO-3310	Tyler	ASTM-E11	BS-410	DIN-4188	Cumulative Weight (%)
50 µM	50 Microns	-	-	-	0.050 mm	50%
315 µM	315 Microns	-	-	-	0.315 mm	97%
700 µM	700 Microns	-	-	-	0.700 mm	100%

Marble ground is a prepared natural product. All data are approximate values and do not represent any warranty

November 2024

MAYN

Address: 306 Square Towers, Cairo – Egypt

Phone: +2 0114 333 888 0 / +2 0100 999 0 773

Email: info@mayntrade.com Website: www.mayntrade.com